

SPORTS SURFACES

DATA SHEET

PASTE EP 11

Two-component epoxy adhesive for PVC and rubber flooring

CHARACTERISTICS

Product formulated for gluing PVC and rubber mats on cement and/or asphalt decks. Paste EP 11 may also be used for gluing decorative synthetic grass on cement surfaces.

APPEARANCE

Component A: neutral high-viscosity paste.
Component B: dark low-viscosity liquid.

CHARACTERISTICS OF THE LIQUID PRODUCT

Characteristic	U.M.	Value	Tolerance
Specific weight	Kg/dm ³	1,9	± 0,1
Dry mass residue	%	96	± 3
Dry volume residue	%	91	± 3
Residue at 450°C	%	67	± 3
Brookfield viscosity: (with Brookfield viscosimeter rotor no. 7, speed 5)	mPa·s	400000	± 20000
Mixing ratio (A:B) by weight	-	A:B = 92:0,8	-

LAYING INSTRUCTIONS

Toolings	Thinner	Type of thinner	Cleaning method
Toothed spatula	Ready for use	-	DIL S1

If the product is highly viscose due to low temperatures, dilute Paste EP11 with DIL S1 at a ratio of 1 - 3 % by weight.

LAYING SURFACE

The deck should be clean and dry and should have no loose parts or traces of oil and grease. Remove imperfections and undue roughness before treating so that the deck is perfectly plane and smooth.

CONSUMPTION

Coverage depends on the roughness of the deck and the materials to glue; coverage is in general between 0.5 to 1.5 kg/sq.m.

SPORTS SURFACES

PASTE EP 11

DATA SHEET

APPLICATION INSTRUCTIONS

Ambient temperature: MIN 10°C - MAX 45°C
Ambient relative humidity: MAX 80 %
Laying surface temperature: MIN 5°C - MAX 35°C

HARDENING AT 23°C AND 50% U.R.

Pot life	45' at 23 °C
Time of start setting	5 h
Maximum hardening time	MAX 4 days

PACKAGING INSTRUCTIONS

Colours available	Neutral.
Packaging	A + B = 12 kg

STORAGE INSTRUCTIONS

Storage temperature:	MIN 10°C - MAX 40°C
Stability in the original package:	6 months

IMPORTANT INSTRUCTIONS

Do not apply the product in the case of fog, high humidity levels, rain or frost. The conditions of the deck must be checked to ensure that it is plane, resistant, consistent that the granule grading is correct in order to prevent imperfections on the surface. Repairs and/or filling must be carried out according to the specifications of Casali S.p.A. Check for rising dampness and/or infiltrations, if necessary contact the Technical Office of Casali S.p.A.

SAFETY STANDARDS

Please read the safety data sheet carefully before using this product.

*The data provided by these data sheets are approximate and the Company reserves the right to modify the same for technical reasons, without prior notice. The solutions proposed do not represent all the possible uses but are merely case studies deriving from Casali's installation experience and are therefore intended only for purposes of illustration. The user is exclusively responsible for the way the products illustrated are used, whether properly or improperly, for evaluating in advance the suitability or otherwise of the product for its requirements and exerting the utmost caution in handling chemical products. **Important: to ensure best colour uniformity of surface laid products, we recommend that you use materials from the same production lot as finishing layer. The Technical Office of Casali's Synthetics Division is at your complete disposal for any further specific information or explanations you may require (phone 071 9162095).***

CASALI
SPORT



ο ΕΙΣΑΓΩΓΗ