

SPORTS SURFACES

DATA SHEET

TOP DOPPIO WS

Concentrated coloured acrylic resin based coating for application on Supersoft Doppio

CHARACTERISTICS

Top Doppio WS is a concentrated coloured acrylic resin based coating which is the ideal finish for Supersoft Doppio. Thanks to the addition of selected quartz sand and to his special formulation, Top Doppio WS ensures the right roughness, above all for tennis, as well as exceptional elasticity and resistance to UV rays. The Supersoft Doppio system is tested by the ITF (International Tennis Federation) in Speed Class 3 (medium).

APPEARANCE

Coloured thixotropic paste.

CHARACTERISTICS OF THE LIQUID PRODUCT

Characteristic	U.M.	Value	Tolerance
Specific weight	Kg/dm ³	1,26	± 0,1
Dry mass residue	%	55	± 3
Dry volume residue	%	42	± 3
Residue at 450°C	%	26	± 3
Brookfield viscosity (with Brookfield viscosimeter rotor no. 4, speed 5)	mPa·s	20000	± 2000
pH	-	8	± 1

APPLICATION METHOD

Add quartz sand (type 0.1 – 0.3 mm) and clean water (approx. 30% of the total weight of the mixture), mixing slowly until the mixture is perfectly smooth and lump free. The mixture may be mixed by hand or in a cement mixer. Apply the product by rubber squeegee within one or two days.

We recommend applying 2 coatings in the following Top Doppio WS / quartz sand weight ratio.

FIRST COATING = 50:50

SECOND COATING = 50:50

For a slightly smoother finish apply the last layer with a mixing ratio of Top Doppio WS / quartz sand = 60 : 40

LAYING INSTRUCTIONS

Tools	Thinner	Type of thinner	Cleaning tools
Rubber spatula	Approx. 25 - 30% of the total mixture (resin + sand)	Water	Water

LAYING SURFACE

Top Doppio WS should be applied on a perfectly dried and well-levelled Supersoft Doppio layer.

IMPORTANT: resin surfaces are generally waterproof (non-draining) so that the deck must be sloped correctly to ensure rainwater runoff and prevent pooling. Works to correct the deck must be carried out before laying the final covering; if necessary please contact the Technical Office of Casali S.p.A.

SPORTS SURFACES

TOP DOPPIO WS

DATA SHEET

CONSUMPTION

The recommended coverage is at least 0.5 Kg./sq.m. of Top Doppio WS + 0.5 Kg./sq.m. of sand applied in 2 coatings.

APPLICATION INSTRUCTIONS

Ambient temperature: MIN 10°C - MAX 40°C
Ambient relative humidity: MAX 90 %
Laying surface temperature: MIN 5°C - MAX 50°C

DRYING AT 23°C AND R.H. OF 50%

On surface	1 h
To touch	2 h
Interval between coatings	4 h

The times indicated refer to standard laboratory conditions. Curing times are strongly affected by weather conditions; high temperatures and direct sunlight accelerate curing; shade, low temperatures and high levels of humidity slow down curing. In winter, lay the product in the warmer hours of the day. Always allow the coating to dry perfectly before applying the next coating.

PACKAGING INSTRUCTIONS

Colours available	Red (102), Green (201), Dark green (202), Blue (303), Light blue (302), Grey (413), Orange (151), Violet (502), Deep blue (319), Violet (507), Red clay (113) and other on request.
Packaging	40 kg. drums.

STORAGE INSTRUCTIONS

Storage temperature:	MIN 3°C - MAX 40°C
Stability in the original package:	12 months

IMPORTANT INSTRUCTIONS

Do not apply the product in the case of fog, high humidity levels, rain or frost. The conditions of the deck must be checked to ensure that it is plane, resistant, consistent that the granule grading is correct in order to prevent imperfections on the surface. Repairs and/or filling must be carried out according to the specifications of Casali S.p.A. Check for rising dampness and/or infiltrations, if necessary contact the Technical Office of Casali S.p.A.

SAFETY STANDARDS

Please read the safety data sheet carefully before using this product.

CERTIFICATION

Top Doppio WS is tested in accordance with and is compliant to standard EN 1297 (Synthetic coverings for outdoor sports areas - Method of artificial ageing by long term exposure to the combination of UV radiation, elevated temperature and water).

*The data provided by these data sheets are approximate and the Company reserves the right to modify the same for technical reasons, without prior notice. The solutions proposed do not represent all the possible uses but are merely case studies deriving from Casali's installation experience and are therefore intended only for purposes of illustration. The user is exclusively responsible for the way the products illustrated are used, whether properly or improperly, for evaluating in advance the suitability or otherwise of the product for its requirements and exerting the utmost caution in handling chemical products. **Important: to ensure best colour uniformity of surface laid products, we recommend that you use materials from the same production lot as finishing layer. The Technical Office of Casali's Synthetics Division is at your complete disposal for any further specific information or explanations you may require (phone 071 9162095).***

CASALI
SPORT



Rev. 02/2018